



USA:(561) 330-9300

www.thermbond.com
 STELLAR MATERIALS INCORPORATED

EU:+31 (10) 2460264

ENGLISH

Revision 07/08/2002 (Check www.thermbond.com for updates)

FORMULA 9-B

Thermbond Refractories use the patented Stellar Binder System™ for easy and accurate mixing, controlled setting, fast dry-out and heat up, thermal shock resistance and other unique properties. Thermbond chemically bonds to existing fired refractories. CHARACTERISTICS: - Alumina - Silica - Dense - Fast Setting - Fast Curing -

PACKAGING		
Unit Equivalent	Bags: 1	Jugs: 1
Bag Weight*	56 lbs	25.4 kg
Jug Weight*	8 lbs	3.6 kg
Drum Weight*	400 lbs	181.4 kg
Unit Weight*	64 lbs	28.8 kg
Yield / Unit*	0.44 ft ³	0.012 m ³
Units / Ton*	31.45 short	34.66 metric
Board Feet / Unit*	5.3 bd ft	
Wet to Dry Ratio*	13.6% - 14.9%	
Liquid Activator	FORMULA	
Bags Per Pallet	48	
Drums Per Dry Pallet	1	

APPLICATION	
Data based on	Casting

BULK DENSITY**		
As Placed	145 lbs/ft ³	2323 kg/m ³
After 1500F (816C)	135 lbs/ft ³	2162 kg/m ³

MAXIMUM RECOMMENDED SERVICE TEMP**		
Hot Face	3000 F	1649 C

COMPRESSIVE STRENGTH**			
1500F (816C)	2750 psi	193 kg/cm ²	19 N/mm ²
2000F (1093C)	4500 psi	316 kg/cm ²	31 N/mm ²
2500F (1371C)	5000 psi	352 kg/cm ²	34 N/mm ²

PERMANENT LINEAR CHANGE**	
1500F (816C)	-0.29%
2000F (1093C)	-0.60%
2500F (1371C)	-0.94%

TYPICAL CHEMICAL ANALYSIS (After 1500F (816C))**	
Al ₂ O ₃	54.63%
SiO ₂	34.14%
Fe ₂ O ₃	0.86%
P ₂ O ₅	5.55%
Other	4.82%
Total	100.00%

THERMAL CONDUCTIVITY**		
600F (316C)	8.5 Btu-in/hr-ft ² -F	1.23 W/m K
1200F (649C)	9.1 Btu-in/hr-ft ² -F	1.31 W/m K
1800F (982C)	9.5 Btu-in/hr-ft ² -F	1.37 W/m K
2400F (1316C)	10.1 Btu-in/hr-ft ² -F	1.46 W/m K

COLD MODULUS OF RUPTURE**			
1500F (816C)	800 psi	56 kg/cm ²	6 N/mm ²
2500F (1371C)	1200 psi	84 kg/cm ²	8 N/mm ²
2800F (1538C)	1700 psi	120 kg/cm ²	12 N/mm ²

HOT MODULUS OF RUPTURE**			
1500F (816C)	1900 psi	134 kg/cm ²	13 N/mm ²

*Measures are approximate and may vary. For mixing partial units, contact Stellar Materials for specific wet-to-dry ratios. See Installation Guide for more detailed information.

**Test data shown are based on averages subject to normal variation on individual tests, and therefore should not be assumed to be maximum or minimum specifications.

Due to the unique nature of the Stellar binder system, test procedures vary slightly from ASTM. Documentation of these variations is available upon request.