



USA:(561) 330-9300

www.thermbond.com  
STELLAR MATERIALS INCORPORATED

EU: +31 (10) 2460264

ENGLISH

Revision 07/16/2008 (Check www.thermbond.com for updates)

# FORMULA 18-BL

*Thermbond Refractories use the patented Stellar Binder System™ for easy and accurate mixing, controlled setting, fast dry-out and heat up, thermal shock resistance and other unique properties. Thermbond chemically bonds to existing fired refractories. CHARACTERISTICS: - High Purity - Tabular Alumina - Very Dense - Non-Wetting - Fast Setting - Fast Curing*

## PRELIMINARY DATA

### PACKAGING

	Bags: 1	Jugs: 1
Unit Equivalent		
Bag Weight*	74 lbs	33.6 kg
Jug Weight*	8 lbs	3.6 kg
Drum Weight*	400 lbs	181.4 kg
Unit Weight*	82 lbs	37.0 kg
Yield / Unit*	0.44 ft <sup>3</sup>	0.012 m <sup>3</sup>
Units / Ton*	24.51 short	27.02 metric
Board Feet / Unit*	5.3 bd ft	
Wet to Dry Ratio*	10.3% - 11.3%	
Liquid Activator	FORMULA	
Bags Per Pallet	48	
Drums Per Dry Pallet	1	

### APPLICATION

Data based on	Casting
---------------	---------

### BULK DENSITY\*\*

As Placed	185 lbs/ft <sup>3</sup>	2963 kg/m <sup>3</sup>
After 1500F (816C)	180 lbs/ft <sup>3</sup>	2883 kg/m <sup>3</sup>

### MAXIMUM RECOMMENDED SERVICE TEMP\*\*

Hot Face	3300 F	1816 C
----------	--------	--------

### ABRASION RESISTANCE\*\* (ASTM C-704)

After 1500F (816C)	<8 cc loss
--------------------	------------

### MOLTEN METAL CONTACT

- Aluminum - Zinc - Iron - Steel
----------------------------------

### COMPRESSIVE STRENGTH\*\*

1500F (816C)	5000 psi	352 kg/cm <sup>2</sup>	34 N/mm <sup>2</sup>
2500F (1371C)	7000 psi	492 kg/cm <sup>2</sup>	48 N/mm <sup>2</sup>
2700F (1482C)	6000 psi	422 kg/cm <sup>2</sup>	41 N/mm <sup>2</sup>

### PERMANENT LINEAR CHANGE\*\*

1500F (816C)	-0.20%
2700F (1482C)	-0.80%

### TYPICAL CHEMICAL ANALYSIS (After 1500F (816C))\*\*

Al <sub>2</sub> O <sub>3</sub>	93.81%
SiO <sub>2</sub>	0.04%
Fe <sub>2</sub> O <sub>3</sub>	0.13%
P <sub>2</sub> O <sub>5</sub>	3.47%
Other	2.55%
Total	100.00%

### THERMAL CONDUCTIVITY\*\*

600F (316C)	18.2 Btu-in/hr-ft <sup>2</sup> -F	2.62 W/m K
1200F (649C)	15.3 Btu-in/hr-ft <sup>2</sup> -F	2.21 W/m K
1800F (982C)	14.5 Btu-in/hr-ft <sup>2</sup> -F	2.09 W/m K
2400F (1316C)	14.8 Btu-in/hr-ft <sup>2</sup> -F	2.14 W/m K

### COLD MODULUS OF RUPTURE\*\*

1500F (816C)	1200 psi	84 kg/cm <sup>2</sup>	8 N/mm <sup>2</sup>
2700F (1482C)	1350 psi	95 kg/cm <sup>2</sup>	9 N/mm <sup>2</sup>

### HOT MODULUS OF RUPTURE\*\*

1500F (816C)	1200 psi	84 kg/cm <sup>2</sup>	8 N/mm <sup>2</sup>
--------------	----------	-----------------------	---------------------

\*Measures are approximate and may vary. For mixing partial units, contact Stellar Materials for specific wet-to-dry ratios. See Installation Guide for more detailed information.

\*\*Test data shown are based on averages subject to normal variation on individual tests, and therefore should not be assumed to be maximum or minimum specifications.

Due to the unique nature of the Stellar binder system, test procedures vary slightly from ASTM. Documentation of these variations is available upon request.