



USA: (561) 330-9300

www.thermbond.com
STELLAR MATERIALS INCORPORATED

EU: +31 (10) 2460264

ENGLISH

Revision 07/16/2008 (Check www.thermbond.com for updates)

FORMULA 18-B

Thermbond Refractories use the patented Stellar Binder System™ for easy and accurate mixing, controlled setting, fast dry-out and heat up, thermal shock resistance and other unique properties. Thermbond chemically bonds to existing fired refractories. CHARACTERISTICS: - High Purity - Tabular Alumina - Very Dense - Non-Wetting - Fast Setting - Fast Curing

PACKAGING		
Unit Equivalent	Bags: 1	Jugs: 1
Bag Weight*	60 lbs	27.2 kg
Jug Weight*	8 lbs	3.6 kg
Drum Weight*	400 lbs	181.4 kg
Unit Weight*	68 lbs	30.7 kg
Yield / Unit*	0.39 ft ³	0.011 m ³
Units / Ton*	29.59 short	32.61 metric
Board Feet / Unit*	4.6 bd ft	
Wet to Dry Ratio*	12.7% - 13.9%	
Liquid Activator	FORMULA	
Bags Per Pallet	48	
Drums Per Dry Pallet	1	

APPLICATION	
Data based on	Casting

BULK DENSITY**		
As Placed	175 lbs/ft ³	2803 kg/m ³
After 1500F (816C)	165 lbs/ft ³	2643 kg/m ³

MAXIMUM RECOMMENDED SERVICE TEMP**		
Hot Face	3000 F	1649 C

ABRASION RESISTANCE** (ASTM C-704)	
After 1500F (816C)	<16 cc loss

MOLTEN METAL CONTACT	
- Aluminum - Zinc - Iron - Steel	

COMPRESSIVE STRENGTH**			
1500F (816C)	4500 psi	316 kg/cm ²	31 N/mm ²
2000F (1093C)	4500 psi	316 kg/cm ²	31 N/mm ²
2500F (1371C)	9000 psi	633 kg/cm ²	62 N/mm ²

PERMANENT LINEAR CHANGE**	
1500F (816C)	-0.20%
2000F (1093C)	-0.50%
2500F (1371C)	-1.50%

TYPICAL CHEMICAL ANALYSIS (After 1500F (816C))**	
Al ₂ O ₃	91.23%
SiO ₂	0.09%
Fe ₂ O ₃	0.17%
P ₂ O ₅	5.17%
Other	3.34%
Total	100.00%

THERMAL CONDUCTIVITY**		
600F (316C)	18.2 Btu-in/hr-ft ² -F	2.62 W/m K
1200F (649C)	15.3 Btu-in/hr-ft ² -F	2.21 W/m K
1800F (982C)	14.5 Btu-in/hr-ft ² -F	2.09 W/m K
2400F (1316C)	14.8 Btu-in/hr-ft ² -F	2.14 W/m K

COLD MODULUS OF RUPTURE**			
1500F (816C)	1100 psi	77 kg/cm ²	8 N/mm ²
2000F (1093C)	1100 psi	77 kg/cm ²	8 N/mm ²
2500F (1371C)	1700 psi	120 kg/cm ²	12 N/mm ²

HOT MODULUS OF RUPTURE**			
1500F (816C)	1650 psi	116 kg/cm ²	11 N/mm ²

*Measures are approximate and may vary. For mixing partial units, contact Stellar Materials for specific wet-to-dry ratios. See Installation Guide for more detailed information.

**Test data shown are based on averages subject to normal variation on individual tests, and therefore should not be assumed to be maximum or minimum specifications.

Due to the unique nature of the Stellar binder system, test procedures vary slightly from ASTM. Documentation of these variations is available upon request.