



USA: (561) 330-9300

www.thermbond.com
STELLAR MATERIALS INCORPORATED

EU: +31 (10) 2460264

ENGLISH

Revision 08/07/2008 (Check www.thermbond.com for updates)

FORMULA 18-R

Thermbond Refractories use the patented Stellar Binder System™ for easy and accurate mixing, controlled setting, fast dry-out and heat up, thermal shock resistance and other unique properties. Thermbond chemically bonds to existing fired refractories. CHARACTERISTICS: - High Purity - Tabular Alumina - Very Dense - Non-Wetting - Fast Setting - Fast Curing

PRELIMINARY DATA

PACKAGING		
Unit Equivalent	Bags: 2	Jugs: 1
Bag Weight*	39 lbs	17.7 kg
Jug Weight*	8 lbs	3.6 kg
Drum Weight*	400 lbs	181.4 kg
Unit Weight*	86 lbs	38.8 kg
Yield / Unit*	0.45 ft ³	0.013 m ³
Units / Ton*	23.36 short	25.75 metric
Board Feet / Unit*	5.4 bd ft	
Wet to Dry Ratio*	10% - 11%	
Liquid Activator	FORMULA	
Bags Per Pallet	48	
Drums Per Dry Pallet	1	

APPLICATION	
Data based on	Ramming

BULK DENSITY**		
As Placed	190 lbs/ft ³	3044 kg/m ³
After 1500F (816C)	185 lbs/ft ³	2963 kg/m ³

MAXIMUM RECOMMENDED SERVICE TEMP**		
Hot Face	3300 F	1816 C

ABRASION RESISTANCE** (ASTM C-704)	
After 1500F (816C)	<8 cc loss

MOLTEN METAL CONTACT	
- Aluminum - Zinc - Iron - Steel	

COMPRESSIVE STRENGTH**			
1500F (816C)	12000 psi	844 kg/cm ²	83 N/mm ²
2700F (1482C)	14000 psi	984 kg/cm ²	97 N/mm ²

PERMANENT LINEAR CHANGE**	
1500F (816C)	-0.20%
2700F (1482C)	-1.00%

TYPICAL CHEMICAL ANALYSIS (After 1500F (816C))**	
Al ₂ O ₃	93.94%
SiO ₂	0.04%
Fe ₂ O ₃	0.12%
P ₂ O ₅	3.39%
Other	2.51%
Total	100.00%

THERMAL CONDUCTIVITY**		
600F (316C)	18.2 Btu-in/hr-ft ² -F	2.62 W/m K
1200F (649C)	15.3 Btu-in/hr-ft ² -F	2.21 W/m K
1800F (982C)	14.5 Btu-in/hr-ft ² -F	2.09 W/m K
2400F (1316C)	14.8 Btu-in/hr-ft ² -F	2.14 W/m K

COLD MODULUS OF RUPTURE**			
1500F (816C)	2500 psi	176 kg/cm ²	17 N/mm ²
2700F (1482C)	2700 psi	190 kg/cm ²	19 N/mm ²

HOT MODULUS OF RUPTURE**			
1500F (816C)	1700 psi	120 kg/cm ²	12 N/mm ²

*Measures are approximate and may vary. For mixing partial units, contact Stellar Materials for specific wet-to-dry ratios. See Installation Guide for more detailed information.

**Test data shown are based on averages subject to normal variation on individual tests, and therefore should not be assumed to be maximum or minimum specifications.

Due to the unique nature of the Stellar binder system, test procedures vary slightly from ASTM. Documentation of these variations is available upon request.